

Research Article

Open Access

## Biogenic Nanoparticles: An Introduction to what they are and how they are Produced

Nida Tabassum Khan\*, Maham Jamil Khan

Department of Biotechnology, Faculty of Life Sciences and Informatics, Balochistan University of Information Technology Engineering and Management Sciences, (BUIITEMS), Quetta, Pakistan

**Corresponding Author:** Nida Tabassum Khan, Department of Biotechnology, Faculty of Life Sciences and Informatics, Balochistan University of Information Technology Engineering and Management Sciences, (BUIITEMS), Quetta, Pakistan.

E-mail: [nidatabassumkhan@yahoo.com](mailto:nidatabassumkhan@yahoo.com)

**Citation:** Nida Tabassum Khan et al. (2017), Biogenic Nanoparticles: An Introduction to what they are and how they are Produced. Int J Biotech & Bioeng.3:3, 66-70. DOI:10.25141/2475-3432-2017-3.0066

**Copyright:** ©2017 Nida Tabassum Khan et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited

**Received:** March 16, 2017; **Accepted:** April 07, 2017; **Published:** April 29, 2017

### Abstract:

Biogenic nanoparticles are synthesized using biological organisms. The reason for choosing biological bodies is that these organisms can easily be cultured, with high intracellular metal uptake. Besides extracellular secretion of enzymes it offers simple downstream processing for product recovery with the ease of biomass handling. The metabolic activity of these microorganisms enables the extra cellular or intracellular synthesis of nanoparticles utilizing different mode of synthesis. Thus producing biogenic nanoparticles of different kinds

**Keywords:** Virtual, Classroom, Web-Based, Learning, Knowledge

### Introduction:

Biogenic metallic nanoparticles have varied applications in various areas such as chemical engineering, tissue engineering, textile manufacturing, nanomedicine, clinical diagnostics (nanobots), electronics, organ implantations [1] biosensors [2], biological imaging [3], biomarkers, cell labeling etc[4,5]. Though there are many synthetic approaches being utilized to produce such entities but use of biological organisms as potential bio-nanofactories is a novel approach for the production of different nano sized particles [6]. For example cadmium sulphide nanoparticle of size range of 20-200 nm was produced intracellularly in *Klebsiella aerogenes* bacterium [7]. Similarly gold and silver nano sized particles were amalgamated by *Verticillium* sp. and *Fusarium oxysporum* fungus [8] and silver nano crystals of definite size and discrete morphology by *Pseudomonas stutzeri* bacterium [9]. Silver nanoparticles formation by *Verticillium* in which the trapping and bioreduction of silver ions take place on the surface of the fungal cell [10, 11]. On the other hand fungus *Usnea longissima* is involved in the production of antimicrobial usnic acid nanoparticles that can be used for curing dermatophytic infections in humans by the mechanism of nanoemulsion [12].

### Extracellular biological synthesis of biogenic nanoparticles:

Numerous examples of biosynthetic methods for nanoparticles

synthesis are available in literature. These biosynthetic procedures can be categorized as intracellular and extracellular depending on where these nanostructures are produced either within or outside the microbial cells respectively [13]. For example in case of extracellular synthesis, silver nanoparticle of size ranging from 16-40 nanometer with diameter of 27 nanometer was produced by the bacterium *Pseudomonas stutzeri* [14], magnetite ( $Fe_3O_4$ ) or greigite ( $Fe_3S_4$ ) nano crystals by magneto bacteria and the fabrication of siliceous material in diatoms [15]. Several strains of *Fusarium oxysporum* were involved in extracellular fabrication of nanoparticles with the help of hydrogenase enzyme present in the fungal broth. This extracellular enzyme behaves as an electron shuttle in bioreduction with excellent redox properties thus capable of transforming metal ions to nanoparticles [16]. As it is evident that microorganism releases hydroquinones which enables metal ions reduction to their respective nanoparticles thus acting as reducing agents or electron shuttles [17].

### Intracellular biological synthesis of biogenic nanoparticles:

But in case of intracellular nanoparticle synthesis the mechanism is quite different. In intracellular synthesis microorganism transport ions into the microbial cell with the help of an ion transportation system. For example bioreduction of ferric to ferrous is followed by the precipitation of amorphous oxide resulting in successive alteration forming magnetite nanoparticles [15]. Alternatively gold nano sized crystals were produced in human cancerous and

non-cancerous cells [18], exhibiting distinct morphologies as confirmed by scanning microscopy. Therefore this property can be applied in cancer diagnostics. However alkalo thermophilic actinomycete or Thermomonospora sp allows the precipitation of gold nanoparticles outside their cells. Similarly the fungus Aspergillus fumigatus and Colletotrichum sp.is known to produce silver and gold nanocrystals extracellularly [19, 20].Not only microorganisms but plants can also be employed for nanoparticle synthesis that the extracellular fabrication of pure metallic gold and silver particles was achieved by the interaction between the Azadirachta indica (Neem) leaf broth with aqueous chloroauric or silver nitrate respectively [21].

**Biological approach versus Synthetic approach:**

Now a days, synthesis of silver nanoparticle have gained significant attraction because of their distinctive properties and various application like in surface-enhanced scattering[22], nucleotide sequencing[23] , antifungal and antibacterial activities [24,12]. Several synthetic methods are reported for the production of silver nano crystals such as heat decomposition in organic solvents [25], silver ions reduction in aqueous solutions in the presence or absence of stabilizers [26], photo-reduction and chemical reduction in reverse micelles [27,28], and synthetic reduction using radiations [29,30,31]etc. But most of these above mentioned routes are costly and involves the usage of poisonous and dangerous substances which pose serious biological and environmental risks. Therefore there is a necessity to develop

an ecofriendly procedure that applies biological principles in nanoparticle formation i.e. biomimetic approach[32,33,14] such as the application of biological catalysts [34], plants extracts or plant biomass [35,36,37] and fungus [38] , for the fabrication of metallic nano crystals that do not employ the usage of harmful chemical substances. Biological systems such as bacteria, plants, fungi are recognized as suitable candidates for nanoparticles synthesis because of features like rapid growth rate, increased protein expression and bioaccumulation of metal nanoparticles by bioreduction etc [39, 40, 41]. For example it was reported that the treatment of AgNO3 with freeze-dried mycelium of Phoma sp. for 50 hours results in the formation of high concentration of silver nanocrystals of diameter 70nm within the mycelium of the fungus as shown by transmission electron microscopy (TEM). The fungal mycelium had absorbed approximately 13mg of silver as indicated by the adsorption assay [42].

**Mode of nanoparticles synthesis by different biological organisms:**

Biological organisms for instance bacteria, fungi and plants make use of different mechanistic approaches for the assembly of diverse nanoparticles such as by means of bioreduction using different reducing or stabilizing agents that contributes towards the synthesis and stability of nanoparticles. Acidification, bioconjugation, metal ion capping, mineralization, enzymatic catalysis and bioreduction etc are familiar modes used for nanoparticles formation as described in Table 1.

S.no	Biological sources	Mechanism
1	BACTERIA	Specific proteins such as NADH dependent reductase or Nitrate dependent reductase involve in metal ion bioreduction [43,44]
2	AIGAE	Functional groups such as hydroxyl groups plays an important roles in bioreduction and stabilization of nanoparticles[45,46,47,48]
3	FUNGI • Filtrate	Specific reduction enzymes and biomimetic mineralization[17,16]
4	YEAST	Membrane bound and cytosolic oxido reductases and quinones[49]
5	PLANTS	Reducing and stabilizing agents such as secondary metabolites like alkaloids, flavonoids, saponins, steroids, tannins etc[50]

**Table 1. Possible modes of nanoparticle biosynthesis by different biological sources**

### Extracellular nanoparticles synthesis versus Intracellular nanoparticles synthesis:

Extracellular synthesis of nanoparticles is more beneficial because product is easily recovered by simple down streaming without host cell lysis [51]. In addition usages of nanoparticles will be well explained if formed extracellularly [52]. For example synthesis of spherical gold nanoparticles by Geranium plant revealed that the fungal polypeptides and the enzymes found in the plant extract were the reducing agents accountable for metal ion reduction [53]. Further examples includes extracellular synthesis of Zirconia nanoparticles [54], silica and Titania nanoparticles from *Fusarium oxysporum* [55]. On the other hand intracellular process of nanoparticle production enables optimization of the morphology of nanocrystals but recovery and purification of nanoparticles from the biomass is a tedious task and hence analytical equipments and long processing techniques are required [56].

### Conclusion:

Nanotechnology is an advanced technology with impactful future perspectives. With the passage of time it is expected that nanotechnology will solve large scale production problems using nanoscale solutions. The use of biological organisms for the production of nanoparticles is a simple environmental friendly and cost effective process. But there are still a lot of hurdles which needs to be overcome. For example the influence of reducing agents in metal ion reduction which affects the morphological characteristics of nanoparticles, determination of the exact pathway involved in the bio fabrication of nanoparticles, optimization of growth parameters like temperature and light intensity etc, control of shape selectivity and size monodispersity of nanoparticles, devising of less costly recovery techniques to make synthesis process commercially practicable etc.

### References:

- 1.Santhosh Kumar T, Abdul Rahuman A, Rajakumar G, Marimuthu S, Bagavan A, Jayaseelan S, Adduz Zahir A, Elango G and Kamaraj C.(2011) [Synthesis of silver nanoparticles using Nelumbonucifera leaf extract and its larvicidal activity against malaria and filariasis vectors](#). Parasitol Res 108:693-702
- 2.Probin Phanjom, Elizabeth Zoremi D, Jahiril Mazumder, Moumita Saha, Sukanya Buzar Baruah. (2012) [Green synthesis of silver nanoparticles using leaf extract of Myricaesculenta](#). Int. J. of Nano Scand Nanotechnol 3(2):73–79.
- 3.Nagaraj B, Divya TK, Malakar Barasa, Krishnamurthy NB, Dinesh R, Negrila CC.(2012) [Phytosynthesis of gold nanoparticles using Caesalpinia pulcherrima \(Peacock flower\) flower extract and evaluation of their antimicrobial activities](#). Dig. J. of Nanomat and Biostru 7(3):899–905.
- 4.Le AT, Huy PT, Tam LT, Tam PD, Hieu N, Huy T.(2011)[Novel silver nanoparticles: synthesis, properties and applications](#). Int. J. of Nanotechnol 8(3): 278-290.
- 5.Singh R, Singh NH.(2011) [Medical Application of nanoparticles in Biological Imaging, Cell Labelling, Antimicrobial Agents and](#)

- [Anticancer Nano drugs](#). J. Biomed. Nanotechnol 7(4): 489-503.
- 6.Sastry M, Mayya KS and Bandyopadhyay K. (1997) [pH Dependent Changes in the Optical Properties of Carboxylic Acid Derivatized Silver Colloidal Particles](#). Colloids Surf. A 127, 221-228.
- 7.Holmes, Smith, Evans-Gowing, Richardson, Russel, & Sodeau (1995). [Energy-dispersive-X-ray analysis of the extracellular cadmium sulfide crystallites of Klebsiella aerogenes](#) Arch. Microbiol 163, 143–147.
- 8.Sastry M, Patil V and Sainkar SR.(1998) [Electrostatically Controlled Diffusion of Carboxylic Acid Derivatized Silver Colloidal Particles in Thermally Evaporated Fatty Amine Films](#). Phys. Chem. B 102, 1404-1410.
- 9.Klaus-Jeorger, Jeorger R, Olsson, Granqvist. (2001). [Bacteria as workers in the living factory: metal accumulating bacteria and their potential for material science](#). Trends Biotechnol 19, 15–20.
- 10.Mukherjee P, Ahmad A, Mandal D, Senapati S, Sainkar SR, Khan M, Parishcha R, Ajaykumar PV, Alam M, Kumar R and Sastry M. (2001) [Fungus-mediated synthesis of silver nanoparticles and their immobilization in the mycelial matrix: a novel biological approach to nanoparticle synthesis](#). Nano1: 515-9.
- 11.Shankar SS, Ahmad A, Pasricha R and Sastry M. (2003) [Bioreduction of chloroaurate ions by Geranium leaves and its endophytic fungus yields gold nanoparticles of different shapes](#). Journal of Material Chemistry 13, 1822–1826. Bioprocess and Biosystem Engineering 449(8), 224–230.
- 12.Shahverdi AR, Mianaeian S, Shahverdi HR, Jamalifar H and Nohi AA. (2007) [Rapid Synthesis of Silver Nanoparticles Using Culture Supernatants of Enterobacteria: A Novel Biological Approach](#). Process Biochem 42, 919-923.
- 13.Mann S (Ed.). (1996) [Biomimetic Materials Chemistry](#), VCH Press, New York
- 14.Klaus T, Joerger R, Olsson E and Granqvist CG. (1999) [Silver-Based Crystalline Nanoparticles, Microbially Fabricated](#). Proc. Natl. Acad. Sci USA 96, 13611-13614.
- 15.Mann S. (2001) [Biomimetalization, Principles and Concepts in Bioinorganic Materials Chemistry](#), Oxford University Press.
- 16.Durán N, Marcato PD, Alves OL, de Souza GIH, Esposito E. (2005) [Mechanistic aspects of biosynthesis of silver nanoparticles by several Fusarium oxysporum strains](#). J Nanobiotechnology 3: 1-8.
- 17.Ahmad A, Senapati S, Khan MI, Kumar R, Ramani R, Srinivas V, Sastry M.(2003) [Intracellular synthesis of gold nanoparticles by a novel alkalotolerant actinomycete, Rhodococcus species](#).Nanotechnology 14, 824–828.
- 18.Sai Vankataraman JA, Subramaniam C ,Kumar RR, Priya S, Santhosh RT, Omkumar VR, John A, Pradeeto T .(2005) [Langmuir](#) 21, 11562.
- 19.Bhanska KC, D Souza SF. (2006) [Coll. Surf. B](#) 47, 160.
- 20.Mandal D, Bolander ME ,Mukhopadhyay D, Sarkar G, Sarkar G, Mukherjee P.(2006) [Appl. Microbiol.Biotechnol](#) 69: 485.
- 21.Shankar S., Rai A., Ahmad A., Sastry M. (2004) [J. Colloid Inter. Sci](#) 275, 496.
- 22.Matejka P, Vlckova B, Vohlidal J, Pancoska P and Baumuruk V. (1992) [The Role of Triton X-100 as an Adsorbate and a Molecular Spacer on the Surface of Silver Colloid: A Surface-Enhanced](#)

Raman Scattering Study. J. Phys. Chem 96, 1361-1366.

23. Cao YW, Jin R and Mirkin CA. (2001) [DNA-Modified Core-Shell Ag/Au Nanoparticles](#). J. Am. Chem. Soc 123, 7961-7962.

24. Baker C, Pradhan A, Pakstis L, Pochan DJ and Shah SI. (2005) [Synthesis and Antibacterial Properties of Silver Nanoparticles](#). J. Nanosci. Nanotechnol. 5, 224-249.

25. Esumi K, Tano T, Torigoe K and Meguro K. (1990) [Preparation and Characterization of Biometallic Pd-Cu Colloids by Thermal Decomposition of Their Acetate Compounds in Organic Solvents](#). J. Chem. Mater 2, 564-567.

26. Lara HH, Garza-Trevino EN, Ixtapan-Turrent L, and Singh DK. (2011) [Silver nanoparticles are broad-spectrum bactericidal and virucidal compounds](#). Journal of Nanobiotechnology vol. 9, no. 30, pp. 2-8.

27. Sun YP, Atornigijawat P and Meziani MJ. (2001) [Preparation of Silver Nanoparticles via Rapid Expansion of Water in Carbon Dioxide Microemulsion into Reductant Solution](#). Langmuir 17, 5707-5710.

28. Pileni MP. (2000) [Fabrication and Physical Properties of Self-Organized Silver Nanocrystals](#). Pure Appl. Chem 72, 53-65.

29. Henglein A. (1998) [Colloidal Silver Nanoparticles: Photochemical Preparation and Interaction with O<sub>2</sub>, CCl<sub>4</sub>, and Some Metal Ions](#). Chem. Mater 10, 444-446.

30. Henglein A. (2001) [Reduction of Ag \(CN\)<sup>-2</sup> on Silver and Platinum Colloidal Nanoparticles](#). Langmuir 17, 2329-2333.

31. Henglein A. (1993) [Physicochemical Properties of Small Metal Particles in Solution: 'Microelectrode' Reactions, Chemisorption, Composite Metal Particles, and the Atom-to-Metal Transition](#). Phys. Chem. B 97, 5457-71.

32. Nair B. and Pradeep T. (2002) [Coalescence of Nanoclusters and Formation of Submicron Crystallites Assisted by Lactobacillus Strains](#). Cryst. Growth Des 2, 293-298.

33. Konishi Y and Uruga T. (2007) [Bioreductive Deposition of Platinum Nanoparticles on the Bacterium Shewanella algae](#). J. Biotechnol 128, 648-653.

34. Willner I, Baron R and Willner B. [Growing Metal Nanoparticles by Enzymes](#). J. Adv. Mater., 18, 1109-1120.

35. Jae YS and Beom SK. (2009) [Rapid Biological Synthesis of Silver Nanoparticles Using Plant Leaf Extracts](#). Bioprocess Biosyst. Eng 32, 79-84.

36. Chandran SP, Chaudhary M, Pasricha R, Ahmad A, Sastry M. (2006) [Synthesis of gold nanotriangles and silver nanoparticles using Aloe Vera plant extract](#). Biotechnol Prog 22(2): 577-583.

37. Shankar SS, Ahmad A, Pasricha R, Sastry M. (2013) [Bioreduction of chloroaurate ions by Geranium leaves and its endophytic fungus yields gold nanoparticles of different shapes](#). Journal of Material Chemistry 13: 1822-1826.

38. Vigneshwaran N, Ashtaputre M, Nachane RP, Paralikar KM, Balasubramanya H. (2007) [Biological synthesis of silver nanoparticles using the fungus Aspergillus flavus](#). Material Letters 61(6): 1413-1418.

39. Khambhaty Y, Mody K, Basha S, Jha B. (2009) [Kinetics, equilibrium and thermodynamic studies on biosorption of hexavalent chromium by dead fungal biomass of marine Aspergillus niger](#). Chem Eng J 145: 489-495.

40. Vala AK, Upadhyay RV. (2008) [on the tolerance and accumulation of arsenic by facultative marine Aspergillus sp.](#) Res J Biotechnol 366-368.

41. Vala AK. (2010) [Tolerance and removal of arsenic by a facultative marine fungus Aspergillus candidus](#). Bioresour Technol 101: 2565 -2567.

42. Chen JC, Lin ZH, Ma XX. (2003) [Evidence of the production of silver nanoparticles via pretreatment of Phoma sp 32883 with silver nitrate](#). Letters in Applied Microbiology 37: 105-108.

43. [Nanotechnology 17: 3482- 3489](#).

44. Durán N, Marcato PD, Durán M, Yadav A, Gade A, Rai M. (2011) [Mechanistic aspects in the biogenic synthesis of extracellular metal nanoparticles by peptides, bacteria, fungi, and plants](#). Appl. Microbiol. Biotechnol 90, 1609-1624.

45. Mishra S, Dixit S, Soni S. (2015) [Methods of nanoparticles biosynthesis for medical and commercial applications](#). Bio-Nanopart. Biosynth. Sustain. Biotechnol. Implic 141-154, doi:10.1002/9781118677629.ch7

46. Azizi S, Ahmad MB, Namvar F, Mohamad R. (2014) [Green biosynthesis and characterization of zinc oxide nanoparticles using brown marine macroalga Sargassum muticum aqueous extract](#). Mater. Lett 116, 275-277.

47. Azizi, S, Namvar F, Mahdavi M, Ahmad MB, Mohamad R. (2013) [Biosynthesis of silver nanoparticles using brown marine macroalga, Sargassum muticum aqueous extract](#). Materials 6, 5942-5950.

48. Ghodake G, Lee DS. (2011) [Biological synthesis of gold nanoparticles using the aqueous extract of the brown algae Laminaria japonica](#). J. Nanoelectron. Optoelectron 6, 268-271.

49. Mahdavi M, Namvar F, Ahmad MB, Mohammad R. (2014) [Green biosynthesis and characterization of magnetic iron oxide \(Fe<sub>3</sub>O<sub>4</sub>\) nanoparticles using seaweed \(Sargassum muticum\) aqueous extract](#). Molecules 18, 5954-5964.

50. Botham KM, Mayes PA. (2006) [Biologic Oxidation](#). In Harper's Illustrated Biochemistry, 28th ed.; Lange-McGraw Hill: London, UK, p. 47.

51. Kuppasamy P, Yousoff MM, Manian GP, Govindan N. (2014) [Biosynthesis of metallic nanoparticles using plant derivatives and their new avenues in pharmacological applications—An updated report](#). Saudi Pharm. J doi:10.1016/j.jsps.2014.11.013

52. Naveen KSH, Kumar G, Karthik L, and Rao KBV. (2010) [Extracellular biosynthesis of silver nanoparticles using the filamentous fungus penicillium sp.](#) Archives of Applied Science Research vol. 2, no. 6, pp. 161-167.

53. Sharma VK, Yngard RA, and Lin Y. (2009) [Silver nanoparticles: green synthesis and their antimicrobial activities](#). Advances in Colloid and Interface Science vol. 145, no. 1-2, pp. 83-96.

54. Shankar SS, Ahmad A, Pasricha R and Sastry M. (2003) [Bioreduction of chloroaurate ions by Geranium leaves and its endophytic fungus yields gold nanoparticles of different shapes](#). Journal of Material Chemistry 13, 1822-1826. Bioprocess and Biosystem Engineering 449(8), 224-230.

55. Bansal V, Rautray D, Ahmad A and Sastry M. (2004) [Biosynthesis of zirconia nanoparticles using the fungus Fusarium oxysporum](#). Journal of Materials Chemistry 14, 3303-3305.

56. Bansal V, Rautray D, Bharde A, Ahire K, Sanyal A, Ahmad A, Sastry M. (2005) [Fungus-mediated biosynthesis of silica and Titania particles](#). Journal of Material Chemistry 15: 2583-2589

---